



PRODUCT DESCRIPTION

#924 Eterna-Sil Premium Silicone Roof Coating is a professional grade 100% silicone roof coating. This product is a high performance, solvent free, high solids, single component, moisture cure liquid applied silicone roof coating. #924 Silicone is an elastomeric and vapor permeable membrane exhibiting outstanding ponded water resistance for direct-bond application over architectural surfaces such as low-sloped or flat roofing systems, vertical walls, masonry, granulated BUR/Mod-Bit, granulated APP, concrete, metal, single-ply membranes and spray polyurethane foam (SPF) systems.

SPECIFICATIONS, APPROVALS + COMPLIANCE

#924 is independently tested and complies and/or exceeds all the requirements of ASTM D 6694 **Standard Specification Liquid-Applied Silicone Coating used in Spray Polyurethane Foam Roofing Systems**. Approved and listed UL and approved under the Florida Building Code. Approvals and certifications are currently in process and pending for Energy Star, Miami-Dade, FM, and P151 Rainwater Catchment. CRRC initial and accelerated values are published and are pending 3-year aged values.

PRODUCT LIMITATIONS

Not recommended for use in permanent standing water for periods longer than 72 hours. For applications over bituminous or asphaltic substrates, the use of **Tropical's #996 Bleed Blocker** is recommended to prevent asphalt bleed-through or staining. #924 can be applied directly over most existing, aged single ply membranes including PVC, TPO, EPDM, and Hypalon pending positive results from an in-field adhesion test. Always refer to the manufacturers (**Tropical Roofing Products**) specification for application limitations, procedures, and guidelines.

PHYSICAL PROPERTIES

ETERNA-SIL PREMIUM SILICONE ROOF COATING	
Tensile Strength	>240 psi @ 73°F
Elongation	>270% @ 73° F
Tear Resistance	>23 lbf/in @ 73° F
V.O.C	<50 g/L
Initial Solar Reflectivity	.87
Accelerated Aged Solar Reflectivity	0.80
Initial Emissivity	.90
Initial SRI Value	110

Permeance (Method B)	3.4 perms
Solids by Weight	>96%
Solids by Volume	97%
Tack-Free Time	Less than 8 hours (RH dependent)
Full Cure Time	8-72 hours
Shelf Life**	24 months (un-opened containers) **when stored between 35°-75°F

PONDING WATER

Tropical's #924 Silicone Coating can be applied over properly prepared surfaces that exhibit ponded water, however, The National Roofing Contractors Association (NRCA) considers ponding water an undesirable non-standard roofing practice and recommends that all roof systems be designed and built to ensure positive drainage. (See the NRCA Roofing and Waterproofing Manual). Please contact **Tropical Roofing Products'** Technical Department for any specific questions regarding the application of this product.

FIRE RESISTANCE CHARACTERISTICS

Tropical's #924 Silicone Coating is pending approval for Class "A" Non-Combustible and Class "B" Combustible credentials as tested under UL 790 Spread of Flame procedures over most common roofing substrates and membranes. Contact **Tropical Roofing Products** or refer to the UL directory for specific information.

PREPARATION

Prior to coating, all surfaces must be clean and dry. It may be necessary to power wash and/or primed to enhance adhesion and or limit asphalt bleed through. Refer to the manufacturers specification for all preparation and guidelines.

MIXING PROCEDURES

Do not thin product with solvent or other solutions. Product may separate after shipping and storage, though it may still look mixed. Mix well before using. We recommend the use of a 3/4 horsepower or larger air operated mixer with a blade capable of uniformly mixing the entire container. When product is in 5-gallon pails, use a 3" minimum diameter-mixing blade. Hand mixing with a suitable mixing blade is acceptable. When product is in drums, use a 6" minimum diameter-mixing blade. Containers are packaged with a layer of dry nitrogen, to keep latent moisture from prematurely starting the curing process. Once opened, the product has a pot life of 2-6 hours, depending on relative humidity conditions.





APPLICATION EQUIPMENT

This product may be sprayed, squeegeed, brushed, or rolled. Due to the viscosity of the material, a high-pressure airless paint pump capable of producing a minimum of 3500 PSI at the spray gun head should be used. The pump should have a minimum of 3 gallons per minute output and be fed by a 5:1 transfer pump to prevent cavitation. Always use components rated for pump pressure. Hoses should be BUNA-N jacketed for prevention of moisture contamination. Hoses should have a minimum I.D. of 3/4" and an adequate working pressure. The spray gun should be high pressure (5000 PSI) with reverse-a- clean spray tip, having a minimum orifice of .030 and a 50° fan tip.

DO NOT USE hose that has been used for Acrylics or other waterborne coatings because the liner absorbs moisture and initiates the silicone cure process.

APPLICATION

#924 is intended for use as a direct-bond, single pass silicone roof coating. Apply at a minimum rate of 1.5 gallons per 100 ft² for a minimum Dry Film Thickness (DFT) of 22 mils. The roof and substrate should be prepped per the manufacturers specification prior to coating. Consult **Tropical Roofing Products** technical team for questions regarding other dry film thickness. The coating will be dry-to-touch in 2-8 hours and should be completely cured and a walkable surface in no more than 72 hours depending on weather conditions (such as temperature and humidity).

#11 Ceramic Roofing Granules may be installed in the topcoat to improve aesthetics, traffic resistance and impact resistance. No more than 2.5 gallons per 100 ft² should be applied in a single-pass or application.

RECOATING PROCEDURES

This product may be used to re-coat existing silicone roof coatings and existing acrylic roof coatings. Refer to manufacturers specification for application procedures, roof preparation, installation guidelines.

COVERAGE

Apply at a minimum rate of 1.5 gallons per 100 ft² for a minimum Dry Film Thickness (DFT) of 22 mils. Application rates will vary by surface, porosity, and job conditions. Please consult **Tropical Roofing Products** for total dry film thickness requirements.

PRECAUTIONS

#924 should not be applied at ambient temperatures lower than 40° F. Be sure that all surfaces are not wet or damp and that rain is not forecasted during application window or for at least 1 hour after application has ended.

CLEANUP

Cleanup of spray equipment containing uncured material may be accomplished by flushing with VM&P Naphtha or Rule 66 Mineral Spirits. **Tropical #924** cures by reacting with moisture and should not be left in spray guns, pump equipment and/or hoses for prolonged periods unless equipment contains moisture lock hoses, fittings, and seals. Equipment without these components will transmit sufficient moisture vapor to gradually form cured material on hose walls and at unsealed connections potentially causing an increase in operating pressure and material flow restriction.

SHIPPING INFORMATION

D.O.T. Classification: Roof Coating, Not Regulated NFMC #170080

CONTAINER SIZE	CLASS
5 Gal.	55
50 Gal.	5

ORDERING INFORMATION

Available in 1 and 5-gallon pails, 50-gallon drums, and 250-gallon totes.

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of the issuance and subject to change without prior notice. User must contact TROPICAL ROOFING PRODUCTS (TRP) to verify correctness before specifying or ordering. We guarantee our product to conform to the quality control standards established by TRP. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any, is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY TRP EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE